BIMETAL STRIP STEEL



BONDS THAT HOLD FOREVER.



We are the experts in producing nonseparable material bonds through highly specialized welding processes.

Our expertise in this core competence is based on three fundamental strengths – quality, experience and innovation. State-of-the-art production facilities, decades of experience in welding and the continual quest for improvement are your guarantee of the highest product quality.

Every day our highly qualified employees ensure that our quality standards are met precisely in all three business units:

- > Precision strip steel
- > Bimetal strip steel
- > Band saw blades

The continual quest for improvement combined with the latest technological processes has made Eberle an internationally recognized leader in innovation.

Our corporate policy is

the finest quality and total customer satisfaction.

For your process chain this means:

- Success through increased quality
- Precision in the production process
- Perfection in the finished product





CORE COMPETENCES	4/5
EBERLE BI-/TRIMETALL	
Tailored Strip Steel	6
Hardened Bi-/Trimetal	7
EBERLE BIMETAL STRIP STEEL for	
Band Saw Blades	8
Jig Saw Blades	
Hole Saws	10
Hand Hacksaw Blades	11
TECHNICAL DATA	12/13

YOUR CENTER OF EXCELLENCE FOR WELDING AND HEAT TREATMENT



J. N. Eberle & Cie. is the only manufacturer in the world that can process the backing material, produce the bimetal and manufacture the saw blades for high-performance band saws all under one roof. This unique capability has enabled us to establish a center of excellence in welding and heat treatment. The result is a superior class of premium products.

Core competence - welding

Our decades of experience in welding a wide variety of material combinations in strip form guarantees the quality of the Eberle superior class products. We are able to continually optimize the quality of the welded joints because we have our own in-house expertise in rolling, cutting and edge processing.

We can weld metal strips of various widths and thicknesses for you – discover the quality of our joints for yourself.



Core competence – heat treatment

In addition to welding a wide variety of material combinations, heat treatment is another in-house core expertise of ours. By combining know-how and the latest technologies we are able to achieve the narrowest tolerances in terms of tensile strength and precisely matched microstructure for whatever the particular application is.

Our top-quality bimetal and trimetal products build process reliability into your supply chain and optimize your throughput rates, which together make a decisive contribution to the high quality of your end product.

Tell us the materials you want to combine – we'll make it happen for you.


innovation@eberle-augsburg.de



TAILORED STRIP STEEL

Whether the metal materials are identical or very different – we will weld a wide variety of different dimensions for you. Up to three strips with a maximum total width of 100 mm can be joined together into a continuous special strip to match your needs.

Take advantage of these economical and premium quality alternatives for your products!




Tailored Strip Steel enables the specific properties of various materials to be uniquely combined, providing excellent abrasion resistance. These materials can be used for the most sophisticated purposes in the automotive and textile industries, the knife and scraper segment, too. Tailored Strip Steel also has the potential to significantly reduce your costs, since high cost materials can now be replaced with more affordable types of material.



HARDENED BI-/TRIMETAL

Hardened bi- and trimetal provides an efficient way to increase service life and cut the costs of materials. Working edges with a hardness of up to 1000 HV equip both the bi- and the trimetal with a high abrasion resistance. The increased service life and the opportunity to replace high-cost materials with affordable materials enable you to reduce your expenses considerably.



You can choose from the Eberle materials or specify your individual requirements. Absolute straightness and the narrowest tolerances are fundamental to our approach.

Hardened bi- and trimetal can by nature be used across the most diverse industrial segments. Possible applications include die-cutting, creasing, folding, creping and scraping, among others.



BAND SAW BLADES

High Speed Steel Carrier material Dimensions

Width tolerance

Thickness tolerance

Parallelism

Straightness deviation Flatness deviation Torsion

Surface finish

Hardness

Edge finish

Eberle M42, Eberle M51 PM, Eberle Matrix II Eberle X32CrMoV4-1, Eberle D6A see page 13

'

 $\begin{array}{lll} \text{max. } 1,0 \text{ mm/1 m} & \text{max. } .04 \text{ in/3 ft} \\ \text{max. } 1,0 \text{ } \mu\text{m/mm strip width} & \text{max. } 1,0 \text{ } \mu\text{m/mm strip width} \\ \text{max. } 5^\circ \text{ (reference length 1 m)} & \text{max. } 5^\circ \text{ (reference length 3 ft)} \end{array}$

soft annealed and temper rolled bright rolled

HSS edge: 240 - 320 HV1 Welding zone: max. 420 HV1 Carrier material: 180 - 250 HV1

Edge wire: rectangular



RECIPROCATING AND JIG SAW BLADES

High Speed Steel Carrier material Dimensions

Width tolerance

Thickness tolerance

Parallelism

Straightness deviation Flatness deviation Torsion

Surface finish

Hardness

Edge finish

Eberle Matrix II and on request Eberle D6A and on request see page 13

max. 1,0 mm/1 m max. .04 in/3 ft

 $\begin{array}{ll} \text{max. 1,0 } \, \mu\text{m}/\text{mm} \, \, \text{strip width} & \text{max. 1,0 } \, \mu\text{m}/\text{mm} \, \, \text{strip width} \\ \text{max. 5}^{\circ} \, \, (\text{reference length 1 m}) & \text{max. 5}^{\circ} \, \, (\text{reference length 3 ft}) \end{array}$

soft annealed and temper rolled bright rolled

HSS edge: 240 - 320 HV1 Welding zone: max. 420 HV1 Carrier material: 180 - 250 HV1

Edge wire: rectangular



HOLE SAWS

Material combinations Dimensions

Width tolerance

Thickness tolerance

Parallelism

Straightness deviation Flatness deviation **Torsion**

Surface finish

Hardness

Edge finish

on request on request

 $w \le 1.38 \text{ in: } \pm .0032 \text{ in}$ $w \le 35,0 \, mm: \pm 0,080 \, mm$ $w > 35,0 \, mm: \pm 0,100 \, mm$ $t < 1,60 \, \text{mm}: \pm 0,020 \, \text{mm}$ $t < .063 \text{ in: } \pm .0008 \text{ in}$ $t \ge .063 \text{ in: } \pm .0010 \text{ in}$ $t \ge 1,60 \, mm: \pm 0,025 \, mm$ max. 0,02 mm max. .0008 in

 $W > 1.38 \text{ in: } \pm .0039 \text{ in}$

max. .04 in/3 ft

max. 1,0 µm/mm strip width

max. 5° (reference length 3 ft)


max. 1,0 mm/1 m

max. 1,0 µm/mm strip width max. 5° (reference length 1 m)

soft annealed and temper rolled bright rolled

HSS edge: max. 320 HV1 max. 420 HV1 Welding zone: Carrier material: max. 250 HV1

Edge wire: rectangular



HAND HACKSAW BLADES

Material combinations
Dimensions

Eberle M2 – 51CrV4 and on request Width: 12,700 mm

Width: 12,700 mm
Thickness: 0,600 mm
HSS-Width: 1,400 mm

Width: .500 in Thickness: .024 in HSS-Width: .055 in

Width tolerance Thickness tolerance Parallelism ± 0,100 mm ± 0,020 mm max. 0,01 mm ± .0040 in ± .0008 in max. .0004 in

Straightness deviation Flatness deviation Torsion max. 1,0 mm/1 m max. 1,0 µm/mm strip width max. .04 in/3 ft max. 1,0 µm/mm strip width max. 5° (reference length 3 ft)

Surface finish

soft annealed and temper rolled bright rolled

max. 5° (reference length 1 m)

Hardness

HSS edge: 240 - 320 HV1
Welding zone: max. 420 HV1
Carrier material: 180 - 250 HV1

Edge finish

Edge wire: rectangular

TECHNICAL DATA

Eberle Grades

High Speed Steel (HSS)

Eberle Grade	Eberle M2	Eberle Matrix II	Eberle M3-1	Eberle M42	Eberle M51 PM			
DIN-Standard	HS6-5-2	HS1-5-1-8	HS6-5-2C	HS2-10-1-8	HS10-4-3-10			
Material-No.	1.3343	1.3270	1.3342	1.3247	1.3207			
AISI-Standard	M2	Matrix II	M3 Class 1	M42	M51 PM			
Elements		Composition (weight-%)						
С	0,85	0,73	1,05	1,05	1,28			
Si	0,30	0,25	0,35	0,30	0,43			
Mn	0,35	0,25	0,30	0,35	0,28			
Cr	4,10	4,10	4,10	3,90	4,15			
Мо	5,00	5,00	5,50	9,50	3,50			
V	1,90	0,95	2,50	1,25	3,25			
W	6,10	1,00	6,00	1,60	9,85			
Со		8,00		8,25	10,00			

Carrier Material

Eberle Grade	Eberle 51CrV4	Eberle 6135	Eberle D6A	Eberle X32CrMoV4-1			
DIN-Standard	51CrV4	35CrV4	49CrMoNiV4-10	X32CrMoV4-1			
Material-No.	1.8159	1.8190	1.7791	1.2390			
AISI-Standard	6150	6135	D6A				
Elements	Composition (weight-%)						
С	0,51	0,35	0,46	0,32			
Si	0,30	0,30	0,20	0,30			
Mn	0,90	0,75	0,75	1,00			
Cr	1,05	0,95	1,00	3,90			
Мо	[1,00	1,10			
V	0,17	0,20	0,11	0,35			
Ni	[0,55	0,70			

TECHNICAL DATA

Eberle Material Combinations and Standard Dimensions

Bimetal Strip Steel for Band Saw Blades

Eberle Grade		Width		Thickness		HSS-Width	
HSS-Wire	Carrier Material	mm		mm		mm	
		6,350	.250	0,889	.035	1,016	.040
		9,520	.375	0,635	.025	1,016	.040
		9,520	.373	0,889	.035	1,016	.040
		10.700	F00	0,635	.025	1,016	.040
		12,700	.500	0,889	.035	1,016	.040
		19,050	.750	0.889	.035	1,016	.040
Eberle	Eberle	19,000	.730	0,889	.033	1,575	.062
M42	X32CrMoV4-1	27,508	1.083	0,889	035	1,016	.040
		27,000	1.000	0,009	.035	1,575	.062
		34,544	1.360	1,067	.042	1,575	.062
		41,525	1.635	1,270	.050	1,575	.062
		54,500	2.145	1,270	.050	1,575	.062
			2.140	1,600	.063	2,000	.079
		67,500	2.657	1,600	.063	2,000	.079
		80,400	3.165	1,600	.063	2,000	.079
		27,508	1.083	0,889	.035	1,575	.062
		34,544	1.360	1,067	.042	1,575	.062
Eberle	Eberle	41,525	1.635	1,270	.050	1,575	.062
M51 PM	X32CrMoV4-1	54,500	2.145	1,600	.063	2,000	.079
		67,500	2.657	1,600	.063	2,000	.079
		80,400	3.165	1,600	.063	2,000	.079
		12,700	.500	0,508	.020	1,016	.040
	Eberle D6A	27,508	1.083	0,889	.035	1,016	.040
Eberle Matrix II			1.000	0,000	.000	1,575	.062
IVIALITA II		34,544	1.360	1,067	.043	1,575	.062
		41,525	1.635	1,270	.050	1,575	.062

Bimetal Strip Steel for Hand Hacksaw Blades

Eberle Eberle M2 51CrV4	12,700	.500	0,600	.024	1,400	.055	
----------------------------	--------	------	-------	------	-------	------	--

Bimetal Strip Steel for Reciprocating and Jig Saw Blades

Eberle Eberle Matrix II D6A	8,000 .315	1,000	.039	1,016	.040	
		.315	1,270	.050	1,575	.062
	19,050		0,889	.035	1,016	.040
		.750	0,889	.035	1,575	.062
			1,270	.050	1,575	.062
	05.400	1 000	1,270	.050	1,575	.062
		25,400	1.000	1,530	.060	1,575

Further material combinations and dimensions on request.

J. N. Eberle & Cie. GmbH

Eberlestr. 28 D-86157 Augsburg Tel.: +49 (821) 5212-0 Fax: +49 (821) 5212-300 bandstahl@eberle-augsburg.de www.eberle-augsburg.de

Eberle America, Inc. 6311 Ronald Reagan Drive Suite 174 USA - 63667 Lake St. Louis, MO Tel.: +1 (314) 406-1102 Fax: +1 (636) 240-6155 strip@eberle-america.com

Eberle Steel Service North America

Regal Steel & Co. 2220 Morrissey USA - 48091 Warren, MI Tel.: +1 (586) 756 -8300 Fax: +1 (586) 756-1845 regal@eberle-america.com

Eberle France

20, Boulevard des Nations F-69960 Corbas Tel.: +33 (4) 78 96 07 53 Fax: +33 (4) 78 96 97 67 strip@eberle-france.com www.eberle-france.com

Eberle Italia S.r.l.

Via Umbria 3/D I-20098 San Giuliano Milanese Tel.: +39 (02) 98 28 17 17 Fax: +39 (02) 98 28 01 78 strip@eberle-italia.com www.eberle.it



J.N. Eberle & Cie. GmbH, Augsburg, Germany Cold Rolling Mill and Saw Factory Quality products since 1836